# Paints, Plasters & Putties



## **Marmix S40 Glossy**

MARMOX S40 Glossy is economic, glossy lacquer (white and colors).

## **General Specifications:**

- MARMIX S40 Glossy is a glossy synthetic paint, based on alkyd and multiple high-quality additives.
- MARMIX S40 Glossy has a high coverage and withstands different weathering conditions.
- MARMIX S40 Glossy is easy to apply and use.

#### Fields of Use:

- MARMIX S40 Glossy is used as a finish on internal surfaces (wooden, metal and cement) after preparing them with a suitable primer.

## **Technical Characteristics:** (at 25 ° C):

Color: White and Colors

Density (gm./cm $^3$ ): 1,0 ± 0.1 Solid Content: 45 ± 5 % Viscosity (4 / FC) 5 – 8 minutes Surface Drying Time at Humidity of 55%: 4 – 5 hours Final Drying Time: 10 – 12 hours

Next Coat Painting Time: 24 hours

Dilution: Mineral Oil or Turpentine or kemsolve7

Theoretical Spreading Rate:  $9 - 11 \text{ m}^2 / \text{kg} / 40 \text{ micron}$ 

### **Method of Application:**

- Clean surfaces well from dust, oils, grease or any other contaminations.
- Smoothen surfaces with putty and then a suitable undercoat such as Kim Lux 333 or diluted Marmix S40 Matt, and finish with at least two coats of MARMIX S40 Glossy.
- Dilute MARMIX S40 Glossy with KIMSOLVE 7 to obtain the suitable consistency.
- Paint with a brush, roller or spraying gun.

**N.B.** To avoid color deviation from one batch to another, only use the same batch number in the same area, In the case of necessity to work with a different batch, apply one package and the color is checked before working with the rest of the quantity.

**Spreading Rate:** 5 – 7 m<sup>2</sup> / liter (Actual coverage rate depends on various factors such as color, the surface condition, and paint coat thickness,

**Storage and shelf/life:** For 2 years from the date of production, provided that the pack is closed and stored away from direct sun rays.

Packs: 0,2 / 0.4 / 0.7 / 2.150 / 4.150 liter.

Headquarters: 319 – 43 Al Haram St. – Giza

Tel.: 35854118 - 35854084 - 35853917 Fax: 35859858

Email: cmb@cmbegypt.com www.cmb.eg

