

Addibond 69

Multi - Use Adhesive for Mortar and Concrete.

Description:

- **ADDIBOND 69** is a versatile adhesive with a wide range of applications. It is latex dispersion admixture based on styrene butadiene rubber and is used for improving the properties of cement mortar and concrete, specifically with regards to bond strength to different building materials, and impermeability to water.
- Complies with ASTM C 631, CMBI TECH. SPCS. No. CMBI 2013.

Fields of Use:

- As an admixture for producing **ADDIBOND 69** slurry, which is used for bonding fresh to old concrete, cement plastering on smooth concrete surfaces, and cement screed topping on concrete flooring.
- As an admixture for producing **ADDIBOND 69** mortar, which is used for the repairing of concrete structures, hard wearing screed toppings high quality plastering and adhering of ceramic tiles to floors and walls.
- Diluted **ADDIBOND 69** can be used as dustproof and surface hardener for concrete and cement plastering surfaces.

Advantages:

- Increases the bond strength of concrete and mortar to different building materials.
- Increases the strength properties, especially tensile and bending strength.
- Increases the elasticity and reduces shrinkage cracking.
- Improves the workability and decreases the mixing water.
- Improves the impermeability of cement mortar and increases resistance to chemicals and salts when added in high dosage to get a water proofing mortar.
- Has no harmful effect.

Technical Data : (at 25 °C)

Colour	White
Soild content	36 ± 2%
Density	1 ± 0.01 kg/ l
Type of latex stabilizer	Non-ionic
PH - Value	8 ± 0.5
Minimum application temperature	4°C

Directions for Use:

(1) ADDIBOND 69 - Slurry:

- Dilute **ADDIBOND 69** with clean water 1 : 3 and mix with cement (or cement and fine sand) and stir thoroughly to form the slurry with the required consistency, spread the bond coat over the area to be bonded. Place the topping or plastering while the bonding application is still wet.
- Consumption 0.25 kg/m².

(2) ADDIBOND 69 - Mortar: (for screeds and repairing works)

- Add **ADDIBOND 69** - diluted with water 1: 4 to 1: 6 to the dry mixed mortar to form a workable paste.
- **ADDIBOND 69** - mortar or concrete should be applied over a wet coat of **ADDIBOND 65** slurry.
- Consumption 30 - 40 kg/m² .

(3) ADDIBOND - Dustproof and surface hardener

- Apply by spray or brush one coat of **ADDIBOND 69** diluted with water at ratio 1 : 4 on the clean surface and allow to dry .Apply a second coat of **ADDIBOND 69** diluted with water at ratio 1 : 2.
- Consumption 0.50 kg/m².

Cleaning of Tools:

- All application tools should be cleaned with water directly after use.

Safety Precautions:

- Wear gloves and goggles.
- Skin and face contamination should be washed with water and soap.
- Accidental splashes to eyes must be rinsed with clean water and then report to an specialist.
- Do not eat and smoke during use.

Storage / Shelf life:

- 12 Months under suitable storage conditions.

Packages:

- 0.9 Kg, 4 kg, 20 kg and 125 kg.