

## Kemapoxy 165 GLV

2 Components Flexible, Low Setting Adhesive.

### Description:

- **KEMAPOXY 165GLV** is two components, solvent free and slow drying adhesive on the basis of epoxy polyurethane resins and selective additives.
- Complies with BS EN 12004, ES 4118.

### Fields of Use:

- Rubber flooring adhesive.
- General purpose flexible adhesive.

### Advantages:

- Can be easily applied.
- Strong adhesion to the substrate.
- Produces an elastic adhesive layer that resists the effect of movement of structure elements.

### Technical Data : (at 25 °C)

Colour	Beige
Solid content	100%
Density	1.46±0.02 kg/l
Mixing ratio A:B (by weight)	8.35 : 1
Pot life	60 minutes
Final setting time	48 hours
Full hardness	7 days
Min application temperature	5°C
Rate of use (on levelled surfaces)	0.6kg±0.1 kg/m <sup>2</sup>

### Directions for Use:

- The substrate should be free from oil, grease, rust, loose particles...etc.
- Mix the two components thoroughly for a period of 2-3 minutes, using a slow rotating electric mixer. (300r.p.m).
- Apply **KEMAPOXY 165GLV** by means of a toothed trowel.
- Wait for a period about 30-40 minutes.
- Place tiles on boards then should be pressed using a suitable metallic roller.

### Safety Precautions:

- Application should be carried out in a well ventilated place.
- Gloves, protective clothing and eye goggles should be worn during application.
- Skin contaminations should be immediately cleaned with soap and plenty of water.
- If the material is splashed into the eyes, these should be washed immediately with water, and then report to an eye specialist.
- Do not eat or smoke during use.

### Storage:

- 2years under suitable storage conditions,in closed containers.

### Packages:

- A kit of two components 6 kg.