

PRIMER CEROPLAST 350 S

Primer for Joint Sealant Ceroplast 350 S.

Description:

- **PRIMER CEROPLAST 350 S** is a one component low viscosity solvent containing product based on bitumen.

Fields of Use:

- Primer for Joint Sealant Ceroplast 350 S.
- For horizontal, vertical and inclined joints.
- For exterior and interior joints.

Technical Data : (at 25 °C)

Density	0.9 ± 0.05 kg/L
Viscosity	2 poise
Solid content	45 - 50 %
Initial drying time	4 hours
Final drying time	24 hours
Rate of use	About 2.5 % of used Ceroplast 350 S

Directions for Use:

- The sides of the joints must be sound, dry and free from oils, grease, dust.....etc.
- The material must be stirred well before use.
- A single coat is applied with a brush .
- The tools used should be washed with kerosene after painting .

Storage / Shelf life:

- 12 months under suitable storage conditions and in closed containers.

Packages:

- 3 kg and 15 kg.