

## Cetokole 300 N

Hot – Poured bituminous rubberized joint sealant

### Description:

- **CETOKOL 300 N** is a hot- poured compound used for sealing joints and cracks in concrete industrial floors highways and airfield pavements.
- **CETOKOL 300 N** does not flow from joints and remains plastic under extreme climatic conditions .
- **CETOKOL 300 N** for ordinary joints complies with federal spec. SS-S 164 & SS-S 200 E for adhesion and water permeability tests .

### Technical Data :(at 25 °C)

Base	Rubber modified bitumen
Colour	Black
Density	1.3 + 0.05 kg/L
Maximum heating temperatures	180 °C
Pouring temperature	160 °C – 180 °C

### Directions for Use:

- Remove **CETOKOL 300 N** from its container and cut into smaller pieces with a hot spade .
- Put the cut pieces in melting container and stir continuously during heating , it is highly recommended to use a special oil melter equipped with stirrer and thermostatic temperature control .
- **CETOKOL 300 N** should not be heated higher than the maximum heating temperatures (180 °C ) otherwise it will loose its plastic properties after cure.
- The joints must be thoroughly dried and cleaned of all dirt , dust grease etc. before applying **CETOKOLE 300 N**.
- Do not melt larger quantity of material than that required for immediate use . Reheating of left-over material **CETOKOL 300 N** is not recommended . Remove any excess material with a hot spade .
- Apply enough material to fill the joints in one or two operations. Remove any excess material with a hot spade .

### Joint size & Estimation of Quantity :

- For joint widths (W) less than 15 mm use depth (D) = 1.5 W .
- For joint width 15 mm and more use  $D = W$  ( minimum 20 mm ) .
- Required Qty . per meter length of joint (kg) =  $D$  (cm) x  $W$  (cm) x density (kg/L) / 10.

### Storage:

- 12 months under suitable storage conditions .

### Packages:

- 20 kg .